



MATERIAL SPECIFICATION SHEET: Neoprene Foam

Dimensions	2m x 1m +- 2%
Thickness	40mm +- 2mm
Type of polymer	CHLOROPENE
Average density	160 kg/m ³
A.S.T.M spec. 1056 D: Grade	2C2
Suffixes	A1 B2 C E1
Heat resistance in °C	
Constant / intermittent	85 / 100°C
Water-absorption: percentage in weight	Below 5%
Compression-deflection: 25% deflection acc. To ASTM spec. 1056D	45 Kpa
Compression-set acc. To ASTM spec. 1056D: 50% compression 22 h at room-temperature: 24 h recovery	10%
Linear shrinkage: 22 h at 70°C	4%
Change in hardness: 7 days at 70°C	15%
22 hours at 100°C	15%
Fluid immersion test acc. to ASTM 1056D spec 7 days at 23°C, change in weight in ASTM Fule "B"	250%
Ozone resistance acc. To spec. DIN53509: 50 pphm ozone concentration 40°C for 48 hours NFR99211: 200 pphm ozone concentration 30°C for 48 hours (in both tests samples elongated by 20%)	No cracking
Fire resistance	Self-extinguish

The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company

Resistance to cold	3
Resistance to air and U.V rays	3
Resistance to dilute acids	3
Resistance to alkalis	3
Resistance to animal or vegetable oils	3
Resistance to solvents: Aliphatic	2
Aromatic	1
Chlorinated	3
Ketonic	1
Resistance to swelling in oil and petrol	3
Acoustic and sound insulation	2

Classification:- 1= nil to weak, 2= average, 3= good, 4= excellent

Shelf Life 10yrs foam, 6 months for adhesive backing before application.

Disposal method is to landfill.

NB: In the same quality, the characteristics of cellular rubber can vary according to numerous factors as: thickness of sheets, sheet with or without moulding skins, methods of tests, etc.....

The information above should be regarded only as a guidance in choice of quality according to the use to which the material is put.