



OIL PAPER JOINTING

Maximum Recommended Service Temperature	120°C	250°F
Colour	Brown	
Compressibility at 70kg/cm ² (1000 psi)	25% - 40%	
Recovery	40% Min.	
Tensile Strength across grain	13.79MN/m ² Min.	
Fluid Resistance Properties after 22 hours at 21°C (70°F) to 30°C (85°F)		
ASTM Oil No.3	Weight increase 15% Max	Thickness increase 5% Max
ASTM Reference Fuel B	Weight increase 15% Max	Thickness increase 5% Max
Distilled Water	Weight increase 90% Max	Thickness increase 30% Max

The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company