



RA3228 PERM/PEEL FILMIC, HIGH-TACK OPEN SIDE DOUBLE-SIDED TAPE, WHITE PAPER LINER

MATERIAL SPECIFICATION SHEET

TECHNICAL DETAILS	TYPICAL VALUE	UNITS
Adhesive + Carrier Thickness	0.070	mm
Release Liner Thickness	0.055	mm
Adhesive Types	Liner side emulsion acrylic, open side hotmelt rubber resin	
180°C Peel Adhesion (Open Side)	1300	N/m
180°C Peel Adhesion (Closed Side)	150	N/m
Polyester Loop Tack (Open Side)	1400	N/m
Polyester Loop Tack (Closed Side)	100	N/m
Liner Release	10	N/m
Tensile Strength	4600	N/m
Elongation At Break	12	%
Service Temperature (Continuous)	-10 to +600	°C
Recommended Application Temperature	+5 to +25	°C
Shear Adhesion (1kg @ 23°C)	>2	Hours
Shelf Life	12	Months



ISO 9001:2015 Q93057

ISO 14001:2015 EMS 505718

The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company