



8070 DOUBLE SIDED TISSUE TAPE SOLVENT ACRYLIC ADHESIVE

MATERIAL SPECIFICATION SHEET

| TECHNICAL DETAILS | TYPICAL VALUE | UNITS |
|-------------------------------------|---------------|--------|
| Adhesive + Carrier Thickness | 0.15 | mm |
| Release Liner Thickness | 0.12 | mm |
| 180°C Peel Adhesion (Open Side) | 900 | N/m |
| 180°C Peel Adhesion (Closed Side) | 900 | N/m |
| Polyester Loop Tack (Open Side) | 1100 | N/m |
| Polyester Loop Tack (Closed Side) | 1100 | N/m |
| Liner Release | 10 | N/m |
| Tensile Strength | 1000 | N/m |
| Elongation At Break | 4 | % |
| Service Temperature (Continuous) | -40 to +140 | °C |
| Service Temperature (Intermittent) | +200 < 1 min | °C |
| Recommended Application Temperature | +5 to +25 | °C |
| Shear Adhesion (1kg @ 23°C) | >50 | Hours |
| Shelf Life | 12 | Months |



The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company