



## AL43 EPDM/NATURAL FOAM

## MATERIAL SPECIFICATION SHEET

Properties	Average value
Density (ASTM D3575)	300 kg/m <sup>3</sup>
Compression Set (23°C ± 2°C) 22h 50% Compression Measured after 24h (ASTM D 1056)	<15%
Shore Hardness "00" Scale	60
Elongation – Minimum (ASTM D 412)	>200%
Temperature Range (Constant)	-30°C to +100°C
Temperature Range (Intermittent)	130°C
Water Absorption Max weight Change (ASTM D 1056)	<2%
Tensile Strength (ASTM D 412)	>1000kPa
Flame Resistance	FMVSS302
Environmental Protection	CFC & HCFC Free

**The above figures are average values and should be considered as guidelines not specifications. We recommend evaluation prior to use to ascertain the suitability of the material for the application.**



The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company