



DK1720 EXPANDED NEOPRENE FOAM RUBBER

MATERIAL SPECIFICATION SHEET

Description	Standard	Value	Unit
ASTM D1056-14 Classification	2C2 B3 M		
Density	ASTM D3575	140-190	Kg/m3
Compression Deflection (25%)	ASTM D1056	35-60	kPa
Compression Deflection (50%)	ASTM D1056	70-120	kPa
Compression Set (25%/22h/23°C) – After 24hrs	ASTM D1056	2-5	%
Compression Set (50%/22h/23°C) – After 24hrs	ASTM D1056	15-35	%
Shrinkage (22h/70°C)	ASTM D573	4-8	%
Shore Hardness		40-50	00
Elongation	ASTM D412	180-220	%
Temperature Range (Constant)		- 40 /+75	°C
Temperature Range (Intermittent)		+90 / +110	°C
Water Absorption (Max Weight Change)	ASTM D1056	1-2	%
Tensile Strength	ASTM D412	500-550	kPa
Flame Resistance (>3mm)	FMVSS302	Pass	
Environmental Protection		CFC & HCFC FREE	



ISO 9001:2015 Q93057 ISO 14001:2015 EMS 505718

The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company