



## DK2015 WHITE EXPANDED EPDM FOAM RUBBER

### MATERIAL SPECIFICATION SHEET

Description	Standard	Value	Unit
ASTM D1056-14 Classification	2A2 B3 M		
Density	ASTM D3575	120-160	Kg/m <sup>3</sup>
Compression Deflection (25%)	ASTM D1056	35-60	kPa
Compression Deflection (50%)	ASTM D1056	60-90	kPa
Compression Set (25%/22h/23°C) – After 24hrs	ASTM D1056	3-5	%
Compression Set (50%/22h/23°C) – After 24hrs	ASTM D1056	15-35	%
Shrinkage (22h/70°C)	ASTM D573	6-9	%
Shore Hardness		35-45	OO
Elongation (Minimum)	ASTM D412	150-200	%
Temperature Range (Constant)		-30 / +80	°C
Temperature Range (Intermittent)		+90 / 100	°C
Water Absorption (Max Weight Change)	ASTM D1056	1-2	%
Flame Resistance (>3mm)	FMVSS302	Pass	
Tensile Strength	ASTM D412	530-600	kPa
Environmental Protection		CFC, HALOGEN & HCFC FREE	



The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company