

FKM 75 O-RING RUBBER

MATERIAL SPECIFICATION SHEET

SPECIFICATION - ASTM D2000 M6HK810 A1-10 B38 EF31 EO88 F15 Z1	Test	Spec	ATSM Method
Original Properties			
Hardness, shore A	77	75 +/-5	D 2240
Tensile Strength, min, MPa	12.5	10	D 412
Elongation, min, %	195	150	D 412
Heat Resistance at 250ºC for 70hrs			D 573
Hardness Change, max, points	+1	+10	
Tensile Change, max, %	-3	-25	
Elongation change, max, %	-11	-25	
Compression Set, Method B			D 395
22 hrs at 200 º C, max, %	14	15	
Fuel C Resistance, 70 hrs at 23ºC			D 471
Hardness Change, points	-4	+/-5	
Tensile Change,max, %	-22	-25	
Elongation Change, max, %	-15	-20	
Volume Change, %	+3	0 to +10	
Blend 7700 Resistance, 70 hrs at 200⁰C			D 471
Hardness Change, points	-8	-15 to +5	
Tensile Change,max, %	-26	-40	
Elongation Change, max, %	-18	-20	
Volume Change, max, %	+18	+25	
Low Temperature Resistance			D 2137
Non brittle after 3 mins at -25°C	Pass	Pass	



1

The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company