

## NITRILE FINE FLUTE

## MATERIAL SPECIFICATION SHEET

PROPERTY	STANDARD	VALUE	UNIT
Elastomer		NITRILE	
		NBR-SBR	
Quality		High Grade	
Colour		Black	
Grade		P9540	
Hardness		65	Shore A (+/-5)
Specific Gravity		1.45	g/cm <sup>3</sup>
Tensile Strength		7	N/mm <sup>2</sup>
Elongation at Break		250	%
Working Temperature		-10 to +70	°C
Working Temperature (Short Term)		+90	°C
Compression Set 22h/+70 °C	DIN ISO 815	40	%
Chemical Resistance	·		
Ozone		Non Resistant	
Weather		Non Resistant	
Oil		Good	
Benzine		Good	
Acid		Moderately Resistant	
Strong Bases		Moderately Resistant	
Abrasion		Non Resistant	
Ageing (70h/70 °C)	·		·
Hardness	DIN 53508	+7	Shore A
Strength	DIN 53508	-10	%
Elongation	DIN 53508	-20	%
Swelling (IRM 903 – 70h/+100 °C)	<u> </u>		
Hardness	DIN 53521	-5	Shore A
Volume	DIN 53521	+10	%

- Excellent ratio of price and performance
- Good oil resistant.
- Good benzene resistant.
- For minor mechanical demands.





ISO 14001 Environmental Management

ISO 9001:2015 Q9305

5 Q93057 ISO 14001:2015 EMS 505718

The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company