

## Data / Specification Sheet • Novus Unifion 51

## **Novus Uniflon 51** is a superior performance biaxially orientated PTFE sheet material with a silica filler

# novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU novus 51 Manufactured by Process bedring Group in the EU

### **Service**

Novus Uniflon 51 is a general purpose grade for sealing applications across the whole pH range. It is particularly suitable for use with strong acids (except hydrofluoric acid) and alkalis. Other applications include solvents, fuels, water, steam, and chlorine. (See the chemical resistance chart for information).

### **Approvals / Compliance**

Conforms with FDA21 CFR 177.1550 regulations.

### **Availability**

Thickness range: 0.75mm to 3.0mm

Standard sheet sizes:

1.0m x 1.0m

1.5m x 1.0m

2.0m x 1.0m

1.5m x 1.5m


2.0m x 1.5m

2.0m x 2.0m

### **Physical properties**

Thickness		1.5mm
Density		2.2g/cc
Tensile Strength	ASTM F152	15MPa
Compression	ASTM F36	7%
Recovery	ASTM F36	40% min
Residual Stress	DIN @ 175°C	32MPa
Creep Relaxation	ASTM F38	23%
Gas Permeability	DIN 3535	<0.01cc/min
Liquid Leakage	ASTM F37	0.21ml/hr

### Novus Uniflon 51 Pressure/Temperature Limits



Suitable subject to chemical compatibility.

2 Suitable in some cases but check your application requirements with Flexitallic.

3 Contact the Technical Team for applications with higher temperatures and pressures. Applicable to 1.5mm and below.

The operating temperature of non-asbestos sheet material is related to the thickness of materials selected. Thinner materials give better temperature and pressure properties.

As the company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only, and without liability on the part of the company.