



OADENSTRONG OIL PAPER JOINTING

MATERIAL SPECIFICATION SHEET

All properties based upon 0.8mm material, refer to ASTM F104 Section 7.

Technical Data:

Property	Test Method	Unit	Value
Moisture Content	15 min @ 100°C	%	8–14
Thickness	ASTM F104	Mm	± 10%
Compression	ASTM F36	%	25-40
Recovery	ASTM F36	%	40 min
Tensile Strength	ASTM F152	Mn/m ²	13.79
IRM 903 Oil Weight Increase	ASTM F146	%	15 max
IRM 903 Oil Thickness Increase	ASTM F146	%	5 max
Fuel B Weight Increase	ASTM F146	%	15 max
Fuel B Thickness Increase	ASTM F146	%	5 max
Water Weight Increase	ASTM F146	%	90 max
Water Thickness Increase	ASTM F146	%	30 max



The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company