



SIL16 SILICONE RUBBER FOAM

MATERIAL SPECIFICATION SHEET

Applications:

Cellular silicone rubber is suitable where a soft, easily deformed rubber is required, for example, for high temperature seals and gaskets. The sheets and punched parts are all available with pressure sensitive adhesive backing to ease assembly.

Thermal Properties:

The range is suitable for continuous use at temperatures up to +200°C. They are also suitable for use at temperatures as low as -60°C.

Chemical Composition:

This range of polydimethylsiloxane has been "free-blown" with a chemical blowing agent and cross-linked with an organic peroxide. The cellular structure is produced without the use of CFC's thus damaging the environment less.

General Information:

Meets the flammability requirements of FAR 25/JAR25/CS 25 Appendix F, Part 1 (a) (1) (iv) and (a) (1) (v) horizontal flammability test and Automotive Standard Part 571FMVSS302.

Closed Cell - can be compressed to meet IP 65.

Brittle Point - 80°C ASTM D746

Limited Oxygen Index - 24.0% BS 2782 Part 2

Thermal Conductivity $6.4 \times 10^{-2} \text{ W.m}^{-1}.\text{K}^{-1}$ BS 874 Part 2

Radiation Resistance $>10^5$ Grays (10^7 Rads) Typically

Moisture Absorption:

The range has a very low degree of moisture absorption.

Mechanical properties shows little change even after long periods of immersion.



ISO 9001:2015 Q93057

ISO 14001:2015 EMS 505718

The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company

Pigmentability:

The product range is available in off-white as standard. Other colours, such as red oxide, are available.

Environmental Resistance:

Silicone rubber has excellent resistance to ozone, oxidation, ultraviolet light, corona discharge, cosmic radiation, ionising radiation and weathering in general. Typical radiation resistance is greater than 10 Grays (greater than 10 rads).

Property	Units	Specification Limits	Typical Value	Test Method
Apparent Density*	Kg/m ³ Lb/ft ³	250 +/- 40 15.6 +/- 2.5	256 16.0	BS EN ISO 845
Hardness**	Shore OO Shore A	- -	45 +/- 5 5	ASTM D 2240
Compression Stress, 40% strain***	kPa psi	90 +/- 40 13 +/- 55.8	90 13	BS EN ISO 3386 Part 1 & 2
Tensile Strength	MPa Psi	0.5 min 72	0.6 87	BS EN ISO 1798
Elongation to Failure	%	100 min	145	BS EN ISO 1798
Compression Set - 50% compression, 24 hours recovery				
22hrs @ 70°C (158°F)	%	15 max	12.0	BS EN ISO 1856
22hrs @ 100°C (121°F)	%	15 max	14.5	BS EN ISO 1856

*Density measured on 25mm diameter cord sample. The density of samples of different sizes will be different from that stated here.

**Hardness measured 10mm thick samples. At less than 10mm the measured hardness will increase with density. The Shore A values are provided as a guideline for comparison to solid materials and as such are not designed for use in specifications.

***Compression set measured on samples as defined in BS EN ISO 3386. The compressive stress on samples of different dimensions, especially thickness may vary from that quoted here.



The company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customer assistance only and without liability on the part of the company